

technical data sheet






EN

Product specifications

| | | |
|-----------------------------|-----------------------|---|
| Multi-Ply Oak wood flooring | EN 14342 (Free Class) | DOP PQ2022-7 |
| Dimensions | Plank | 600 x 120 x 14/ 3 mm |
| | Box | 20 planks / 1,44 m ² / 11 kg |
| | Nested lengths | - |
| | Pallet | 56 boxes / 80,64 m ² / 740kg |
| Density | EN ISO 23996 | +/- 530 kg/m ³ |
| Installation | ISO 24334 | Uniclic HB (floating or glued) |
| Top layer | | 3 mm European oak (Quercus Robur) |
| Grading | | Rustic B |
| Surface | | Slightly brushed |
| Bevel | | Bevel 4V |
| Gloss level | 60° | 5-10% |
| Finishing | | Matt lacquer |
| Warranty conditions | Residential use | 20 years |
| | Commercial use | upon request |
| Application | EN 14342 | Class 23 |



Producteigenschappen

| Property | Test method | min. req. | result |
|---------------------------|--|-----------------------------|--|
| Indoor air certifications | | | A, REACH |
| Fire resistance |  EN 13501-1 | | Dfl-S1 |
| Slip resistance |  EN 13893 | | DS (≥ 0.30) |
| Formaldehyde emission |  EN 717-1 | ≤ 0.124 mg/m ³ | E1 |
| Pentachlorofenol content |  EN 12673 | < 5 ppm | < detectable limit |
| Underfloor heating |  EN 12667 | R < 0.15 m ² K/W | R = 0,135 m ² K/W OK (max +28°C) + glued |
| Biological durability | | | Class 1 |

Cleaning and maintenance instructions: www.lamett.eu

